AZL Otrokovice s.r.o. ,
Zkušebna kožedělných a textilních materiálů a výrobků

tř. Tomáše Bati 1724, 765 02 Otrokovice
tel.:+420 731 174 751; e-mail: stachova@azl.cz; www.azl.cz

The translation - the original Test report has mandatory wording.

TEST REPORT
no. 2003/26

Customer:	**PET HARDWARE s.r.o.**
Customer address:	Grymovská 256/1a, 750 02 Přerov IV - Kozlovice
Order:	order from 05.10.2026
Tested sample:	**Vegetable tanned cowhide leather, colored through, colour black**
Designation of the sample by laboratory - by customer:	2003/26 - des. Origin: Argentina; reprezentative sample of the same type of the leather also available in Brown a Tan colours
Number of samples:	1
Dimension of sample :	1 pc - (27 x 44) mm
Date of sample receipt:	06.10.2026
Date of tests performance:	06.10.2026 - 15.10.2026
Test report	
Number of copies:	2 Copy no. 1- customer; Copy no. 2- laboratory archive
Place and date issuance:	Otrokovice, 15.10.2026
Approved by:	..... **Ing. Jiří Štach** *deputy manager of testing laboratory*

ZKUŠEBNA KOŽEDĚLNÝCH A TEXTILNÍCH MATERIÁLŮ A VÝROBKŮ AZL OTROKOVICE

Conditions for use of the Test Report:
The Report contains test results which apply to the sample received only.
The laboratory will not accept any liability for the sampling process. Sampling was carried out by the customer. The laboratory declines responsibility for information supplied by the customer (sample and designation).
The Report may not be reproduced otherwise than in full without written consent of the laboratory. The customer should obtain consent of the laboratory that issued the Report for reproducing a part of the Report. If the Report contains any tests carried out on the basis of a subcontract, this fact is stated in the Report. The tests were carried out at the permanent address of the laboratory.

AZL Otrokovice s.r.o. ,
Zkušebna kožedělných a textilních materiálů a výrobků

tř. Tomáše Bati 1724, 765 02 Otrokovice
tel.:+420 731 174 751; e-mail: stachova@azl.cz; www.azl.cz

Test report no. 2003/26

Executed tests

Pos.	Name	Method
1	Leather - Chemical determination of chromium (VI) content in leather - Part1: Colorimetric method	ČSN EN ISO 17075-1
2	Leather - Chemical determination of formaldehyde content - Part 2: Method using colorimetric analysis	ČSN EN ISO 17226-2
3	Leather - Chemical tests - Determination of pH and difference figure	ČSN EN ISO 4045

Additional information to executed tests and deviations from method procedure:
Test pieces were conditioned for a minimum of 48 hours in the atmosphere with temperature (23 ± 2) °C and relative humidity (50 ± 5) %.
Detection limit of the method no. 1 is 3 $mg.kg^{-1}$.

RESULTS OF THE TESTS

Tested sample		**2003/26 - Vegetable tanned cowhide leather, colored through, colour black - des. Origin: Argentina; reprezentative sample of the same type of the leather also available in Brown a Tan colours**				
Pos.	**Tested quantity**	Unit of measurements	Limit value [1]	**Determined value [2]**	Uncertainty of measurements [3]	Conformity [4]
1	**Extractible chromium (VI) content** mass fraction of volatile matter - 13,7%	$mg.kg^{-1}$	under the detection limit of the method	**< 3 under the detection limit of the method**	-	**Yes**
2	**Content of formaldehyde**	$mg.kg^{-1}$	max. 30	**10,5**	**8%**	**Yes**
3	**pH of aqueous extract** **Difference figure** (for pH < 3,5)	non-dimensional number	- -	**3,14** **0,58**	0,1 0,1	- -

Explanations to the table:
1) Requirements and specifications -limit values were stated by customer accord with Methodical recommendation of SZÚ no. 1/2000 (tests no. 1, 2).
2) Unless stated otherwise, the determined values are stated as sample arithmetic mean from repeated measurements according to used method.
3) Extended measurement uncertainty - calculated from repeated measurements with aplication of expansion coeficient k=2, which corresponds in normal allocation to the probability of coverage 95 % (tests no. 2-3).

4) Conformity statement/decision making rule: according to ILAC-G8: 09/2019, cl. 4.2.1, A binary statement for the simple acceptance rule
yes - complies with the limit value
no - does not comply with the limit value

Test report drafted and conformity assessment performed: Ing. J. Štach

the end of the Test Report